


Hexa Zircon

Preparation Instructions

A circumferential groove of 0.8 mm should be aimed at. The vertical preparation angle should be 3° - 5° . All transitions from the axial to the occlusal and/or incisal surface should be rounded, smooth, homogeneous surfaces are recommended.



- Occlusal and incisal reduction: 1.5 mm to 2.0 mm.
- Circumferential groove of 0.8 mm.



- No deep holes
- Circumferential groove not like J.
- Die length : 3 mm.

